## **CD Structural**



## Fact Sheet 29

CD Structural manufactured by PNGFP is a quality softwood faced structural panel manufactured to AS/NZS2269 which is suitable for a wide variety of uses.

## **Features and Benefits**

- 100% Plantation pine
- Manufacture using hydro-electric power
- Lightweight and easy to install
- Manufactured to stress grade F14
- Available in size 2400x1200
- Thickness 7,9,12, 15, 17, 19, 21 and 25mm
- Manufacturing standard AS/NZS 2269
- Manufactured with "A-Bond" Phenolic adhesive.

| Surface Finish          | Sanded Face                        |
|-------------------------|------------------------------------|
| Face Grade              | "C"                                |
| Back Grade              | "D"                                |
| Sheet Length            | 2400mm                             |
| Sheet width / cover     | 1200mm                             |
| Sheet Thickness         | 7, 9, 12, 15, 17, 18, 19, 21, 25mm |
| Stress grade            | F14                                |
| Veneer Species          | Plantation Hoop Pine               |
| Approximate Density     | 580 kg/m3                          |
| Jointing System         | Square Edge                        |
| Chain of Custody        | PEFC Controlled wood               |
| Bond type               | "A" Bond (Phenol formaldehyde)     |
| EWPAA Certificate       | Yes                                |
| Manufacturing standards | AS/NZS 2269                        |

Whilst the information contained in this document is based on data which, to the best of our knowledge was accurate and reliable at the time of preparation, no responsibility can be accepted by us for error or omissions. The provision of this information should not be construed as a recommendation t use any of our products in violation of any patent rights or in breach of any statute or regulation. Users are advised to make their own determinations as to the suitability of this information in relation to their particular purpose and specific circumstances. Since the information contained in this document may be applied under conditions beyond our control, no responsibility can be accepted by us for any loss or damage caused by any person acting or refraining from action as a result of this information.