## **Structural**



## Fact Sheet 29

CD Structural manufactured by PNGFP is a quality softwood faced structural panel manufactured to AS/NZS2269 which is suitable for a wide variety of uses.

## **Features and Benefits**

- 100% Plantation pine
- Manufacture using hydro-electric power
- Lightweight and easy to install
- Manufactured to stress grade F14
- Available in size 2400x1200
- Thickness 7,9,12, 15, 17, 19, 21 and 25mm
- Manufacturing standard AS/NZS 2269
- Manufactured with "A-Bond" Phenolic adhesive.

Surface Finish	Sanded Face
Face Grade	"C" or "B"
Back Grade	"D"
Sheet Length	2400mm
Sheet width / cover	1200mm
Sheet Thickness	7, 9, 12, 15, 17, 18, 19, 21, 25mm
Stress grade	F14
Veneer Species	Plantation Hoop or Klinkii Pine
Approximate Density	580 kg/m3
Jointing System	Square Edge
Chain of Custody	PEFC Controlled wood
Bond type	"A" Bond (Phenol formaldehyde)
EWPAA Certificate	Yes
Manufacturing	AS/NZS 2269
standards	

PNG Forest Products Engineered Wood Products are certified by the Engineered Wood Products Association of Australasia (EWPAA) and carry the EWPAA JAS-ANZ brand. The EWPAA operated a Type 5 third party product certification scheme that is accredited by the peak accreditation body JAS-ANZ. This means that any product branded with the EWPAA JAS-ANZ brand has been manufactured under an accredited third party audited; process-based quality control program that ensures the product meets the intended design criteria.





Whilst the information contained in this document is based on data which, to the best of our knowledge was accurate and reliable at the time of preparation, no responsibility can be accepted by us for error or omissions. The provision of this information should not be construed as a recommendation t use any of our products in violation of any patent rights or in breach of any statute or regulation. Users are advised to make their own determinations as to the suitability of this information in relation to their particular purpose and specific circumstances. Since the information contained in this document may be applied under conditions beyond our control, no responsibility can be accepted by us for any loss or damage caused by any person acting or refraining from action as a result of this information.